

FR-M1K



Fire retardant Mono Component Putty

Green product
50gr VOC



Ready to use!
No mixing required



Applicable with
spatula



Fast drying



Quick sanding



How to use it?



FR-M1K



Market place



- OEM
- MRO
- AIRLINES



- Cabin interior repairs
- Composite surface filler



- Water based
- Color Beige & White



- Ideal packaging 400 gr
- No MOQ
- Carton box

Heat Release Results

Analysis



Test standard

AITM 2.0006
(issue 3)

Materials

Paint (Putty - 50µm)
on
Aluminium plate (1mm)

Requirement

ABD0031
(issue F)

Results

Specification
Average

HRR max*
(kW/m)
≤65
18.8

THR 2minutes**
(kW.min/m)
≤65
4

HRR max*: maximum heat release rate within 5 minutes • THR 2minutes**: total heat release at 2 minutes